

Oxidized Bitumen 75/25

Properties	Range	Test Method
Penetration @ 25°C	20-30	ASTM D5
Softening Point°C	70-80	ASTM D36
Ductility @ 25°C	1.5 min	ASTM D113
Flash point °C	250 min	ASTM D92
Specific Gravity @ 25°C	Appr 1	ASTM D70
Loss on Heating (Wt)%	0.2 max	ASTM D6
Solubility in CS ₂ (Wt)%	99 min	ASTM D4

Application

Oxidized Bitumen is mainly used for industrial purposes, such as roof insulation, flooring, industrial mastics, pipe coating, and paints and also roads as waterproofing purposes.

Packing

Poly Bag. Craft Paper. Carton Box. Drum