

## Oxidized Bitumen 90/40

Properties	Range	Test Method
Penetration @ 25°C	35-45	ASTM D5
Softening Point°C	85-95	ASTM D36
Ductility @ 25°C	1.5 min	ASTM D113
Flash point °C	250 min	ASTM D92
Specific Gravity @ 25°C	Appr 1	ASTM D70
Loss on Heating (Wt)%	0.2 max	ASTM D6
Solubility in CS <sub>2</sub> (Wt)%	99 min	ASTM D4

### Application

Oxidized Bitumen is mainly used for industrial purposes, such as roof insulation, flooring, industrial mastics, pipe coating, and paints and also roads as waterproofing purposes.

### Packing

Poly Bag. Craft Paper. Carton Box. Drum